

- As for shower recesses, precut polyester tapes and matting to required lengths and dimensions.
- Apply Boscoseal AC1 into wastes, drains or onto puddle flanges. Boscoseal AC1 must be dressed down into the waste at least 50mm.
- Apply an initial coat of Boscoseal AC1 either side of all wall/floor junctions and sheet flooring joints. Extend the coating at least 100mm either side of the joins.
- Lay polyester tape along corners into wet Boscoseal AC1 and recoat, ensure there is no air entrapment in the tape.
- Repeat the procedure on the floor area.
- Apply an initial coat (It is recommended that areas of only 1-2 M² be applied at any one time) lay and force precut matting into the wet Boscoseal AC1 to ensure complete contact is achieved.
- Immediately recoat, ensuring there is no air entrapment in the matting.
- Allow too dry for at least 24 hours.
- A third coat of Boscoseal AC1 may be necessary if imperfections in the membrane are evident.

8. ROOF APPLICATIONS

Boscoseal AC1 is recommended as a waterproof membrane for non-traffic areas. (Application method is the same as for wet areas, floors and decks). These areas of application should not be accessed until membrane has fully cured.

TILING AND MORTAR BED COVERING

To eliminate possible surface contamination or damage, it is recommended tiling, mortar bed applications or finished flooring installations are carried out as soon as possible after full cure of the membrane. These installations may be carried out after the Boscoseal AC1 two-coat system has been allowed to cure for a minimum of 3 days at 25°C (slightly longer in lower temperatures). Movement joints provided in tiling should be filled with either Bostik Seal'n'Flex 1 or FC polyurethane sealant or Bostik neutral cure anti-fungal silicone sealant.

TILE ADHESIVE

Proprietary commercially available tile adhesives may be used such as Architectural & Structural Adhesives (ASA); ASAFLEX, CONFLEX, MEGAFIX or FIXALL mixed with MEGALASTIC and/or equal, recommended and applied in strict compliance with manufacturer's instructions.

P.A.T.S PROGRAMME (Pretested Adhesion to Substrate)

Bostik offer a service in which a program has been established to eliminate potential field problems by pre-testing Bostik coatings and membranes with samples of building materials to which the systems will be applied. This service is available on large projects where pre-application testing will aid in determining the proper surface preparation method to achieve optimum adhesion. Consult a Bostik representative for further information.

PRECAUTIONS

- Do not apply where the surface temperature is below +10°C or greater than 35°C.
- Boscoseal AC1 is not a vapour barrier nor designed to stop a hydrostatic head of water pressure. (For this application, Bostik Moisture Seal should be used).
- Do not apply on wet (moisture content above 15%), contaminated, or friable substrates.
- Do not apply externally if raining or rain is imminent.
- Do not apply to surfaces with protective coatings without prior consultation with Bostik.
- The rate of cure will be dramatically reduced when air or substrate temperatures are below +10°C or if applied over a vapour barrier or untreated concrete.
- A third coat of Boscoseal AC1 may be necessary if imperfections in the cured membrane are evident.
- The application rate of Boscoseal AC1 should not be extended over the recommended coverage of 1 litre per square metre or under 0.8mm wet film thickness in one application.
- Do not dilute with water or extend with cement powders or other additives.
- Boscoseal AC1 requires atmospheric conditions to cure. It should not be used in totally confined or air free spaces.
- Boscoseal AC1 is not trafficable and should not be used as a wearing surface for foot or vehicle traffic.
- Do not apply over treated pine.
- Totally impervious substrates such as epoxies and rigid fibreglass will require priming.
- To prevent mechanical damage in planter box or tubs, timber or rigid plastic (corflute) sheets must protect the membrane.
- Boscoseal AC membranes must not come in direct contact with polyurethane sealants in any application.
- Any intended use of Boscoseal AC1 outside of specified use should be referred to Bostik technical services for approval.

HEALTH AND SAFETY

- If swallowed, do not induce vomiting. Give a glass of water; contact a doctor or Poisons Information Centre.
- For more detailed information refer to Material Safety Data Sheet.

CLEAN-UP

Boscoseal AC1 can be cleaned from skin and application equipment with water while the membrane is still wet.

STORAGE

Store in original containers under cover in dry conditions. Boscoseal AC1 has a shelf life of 12 months in original unopened containers if stored between 5°C and 35°C. Do not freeze.

ITEM NO.	PRODUCT
301248	Boscoseal AC 1 15 Litre White
301256	Boscoseal AC 2 15 Litre White
298476	Boscoseal AC 3 20 Litre (2 Part Kit) Grey
300217	AC Primer 20 Litre
263362	Moisture Seal 8 Litre (2 Part Kit) Grey
263370	Moisture Seal 20 Litre (2 Part Kit) Grey
227935	5077 Primer 1 Litre Clear
287032	Ultra NP Primer 4 Litre Green
272496	Ultrarapid Set 20 Kg Grey

The representations and recommendations regarding the products are based on tests, which we believe to be reliable. However, no guarantee of their accuracy can be made because of the great range of field conditions and variations encountered in raw materials, manufacturing equipment and methods. Thus, the products are sold with a limited warranty only, and on the condition that purchasers will make their own tests to determine the suitability of the product for their particular purposes. Under no circumstances will Bostik Australia Pty Ltd be liable to anyone except for replacement of the products or refund of the purchase price.

ALL SALES ARE EXPRESSLY LIMITED TO THE TERMS AND CONDITIONS OF SALE OF BOSTIK AUSTRALIA PTY LTD



FOR FURTHER INFORMATION

BOSTIK AUSTRALIA PTY LTD
Phone: +61-3-9279 9333
Fax: +61-3-9279 9240

BOSTIK NZ LIMITED
Phone: +64-4-567 5119
Fax: +64-4-567-5412

BOSTIK SINGAPORE PTE LTD
Phone: +65-863 4088
Fax: +65-863 4077

BOSTIK (MALAYSIA) SDN BHD
Phone: +606 764 3246
Fax: +606 764 3248

SYDNEY
Phone: 02 8825 3488
Fax: 02 8825 3411

ADELAIDE
Phone: 08 8244 0511
Fax: 08 8244 0522

PERTH
Phone: 08 9331 7666
Fax: 08 9331 7677

BRISBANE
Phone: 07 3260 2206
Fax: 07 3260 2123

Product:	Boscoseal AC1
Issue Date:	July 2004
Issue No:	1
Division:	Construction
Total Pages:	4